



## IST & AST SEALANT TAPES

### Wet Sealant Compatibility Chart

# TEST DATA

#### Manufacturer:

##### EMSEAL JOINT SYSTEMS, LTD.

23 Bridle Lane, Suite 3

Westborough, MA 01581-2603

TOLL FREE: 800-526-8365 PH: 508-836-0280 FX: 508-836-0281

##### EMSEAL CORPORATION

84 Brydon Drive

Rexdale, ON, Canada M9W 4N6

TOLL FREE: 866-436-7325 PH: 416-740-2090 FX: 416-740-0233

Manufacturer / Product	Compatibility	Adhesion to Foam
<b>Bostik Construction Products</b>		Yes
Chem-Calk 500	Yes	Yes
Chem-Calk 550	Yes	Yes
Chem-Calk 900	Yes	Yes
<b>Dow Corning</b>		
Dow 790	Yes	Yes
Dow 795	Yes	No
Dow 999	Yes	Yes
<b>General Electric</b>		
Silpruf	Yes	Yes
Gesil N	Yes	Yes
SCS 1200	Yes	Yes
<b>Pecora Corporation</b>		
Dynatrol - I	Yes	Yes
Dynatrol - II	Yes	Yes
Dynatred	Yes	Yes
<b>Sika Corporation</b>		
Sikaflex - 15LM	Yes	Yes
Sikaflex - 2CNS	Yes	Yes
<b>Sonneborn Building Products</b>		
NP1	Not Tested	Yes
NP2	Not Tested	Yes
Omniseal	Not Tested	Yes
Omniplus	Not Tested	Yes
<b>Tremco</b>		
Butyl	Yes	Yes
Dymeric	Yes	Yes
Dymonic	No	Yes
Mono	Yes	Yes
Proglaze	No	Yes
THC 900	Yes	Yes

GENERAL NOTE: Light colored sealants which are installed in direct contact with AST will become dri colored (darkened) over time. Generally IST is chosen in applications where direct application of a liquid sealant is intended.

Individual test reports from sealant manufacturer are available